

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification 6 : D21F 11/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/47749 (43) International Publication Date: 23 September 1999 (23.09.99)</p>
<p>(21) International Application Number: PCT/IB99/00418 (22) International Filing Date: 15 March 1999 (15.03.99) (30) Priority Data: 60/078,301 17 March 1998 (17.03.98) US (71) Applicant (for all designated States except US): THE PROCTER &amp; GAMBLE COMPANY [US/US]; One Procter &amp; Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): TROKHAN, Paul, Dennis [US/US]; 1356 Warvel Road, Hamilton, OH 45013 (US). PHAN, Dean, Van [US/US]; 6512 Tylers Crossing, West Chester, OH 45069 (US). AMPULSKI, Robert, Stanley [US/US]; 5674 Red Oak Drive, Fairfield, OH 45014 (US). (74) Agents: REED, T., David et al.; The Procter &amp; Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).</p>		<p>(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
<p>(54) Title: APPARATUS AND PROCESS FOR MAKING STRUCTURED PAPER AND STRUCTURED PAPER PRODUCED THEREBY</p> <div data-bbox="357 1155 1218 1470"></div> <p>(57) Abstract</p> <p>An apparatus and process for imprinting a web. A yankee drum (70) and pressure roll (35) are juxtaposed to form a nip. An imprinting member (30), such as through air drying belt or other patterning belt is interposed in the nip. A felt (60) is also interposed in the nip, contacting the backside of the imprinting member. The imprinting member carries a paper web (32). The paper web is imprinted in the nip and simultaneously transferred to the yankee drying drum. The nip may be formed with a vacuum roll juxtaposed with the felt. The vacuum roll may remove water from the felt and hence the web.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

APPARATUS AND PROCESS FOR MAKING STRUCTURED PAPER  
AND  
STRUCTURED PAPER PRODUCED THEREBY

FIELD OF THE INVENTION

The present invention relates to papermaking, and more particularly to papermaking which yields paper having regions of different regions, such as density, caliper, crepe, amplitude, etc.

BACKGROUND OF THE INVENTION

Papermaking is a well known art. In papermaking cellulosic fibers and a liquid carrier are mixed together. The liquid carrier is drained away and the resulting embryonic web of cellulosic fibers is dried.

Drying is typically accomplished in one of two manners, through air drying or conventional drying. Through air drying relies upon blowing hot air through the embryonic web. Conventional drying relies upon a press felt to remove water from the web by capillary action.

Through air drying yields paper having regions of different densities. This type of paper has been used in commercially successful products, such as Bounty paper towels and Charmin and Charmin Ultra brands of bath tissues. However, there are or may be situations where one does not wish to utilize through air drying.

In these situations, conventional felt drying is used. However, conventional felt drying does not necessarily produce the structured paper and its attendant advantages. Accordingly, it has been desired to produce structured paper using conventional felt drying. This has been accomplished utilizing a conventional felt having a patterned framework thereon for imprinting the embryonic web. Examples of these attempts in the art include commonly assigned U.S. Patent Nos. 5,556,509, issued Sept. 17, 1996 to Trokhan et al.; 5,580,423, issued Dec. 3, 1996 to Ampulski et al.; 5,609,725, issued Mar. 11, 1997 to Phan; 5,629,052, issued May 13, 1997 to Trokhan et al.; 5,637,194, issued

June 10, 1997 to Ampulski et al.; 5,674,663, issued Oct. 7, 1997 to McFarland et al.; and 5,709,775 issued Jan. 20, 1998 to Trokhan et al., the disclosures of which are incorporated herein by reference.

However, there may be occasions when one wishes to use a conventional felt without a patterned framework thereon. Such flexibility in the manufacturing process is provided by the present invention.

U.S. Pat. 4,421,600 issued December 20, 1983 to Hostetler discloses an apparatus having two felts, and three pressing operations. Again, after pressing the web is transferred on a woven imprinting fabric to the Yankee dryer.

Such an attempt in the art is illustrated by U.S. 4,309,246 issued Jan. 5, 1982 to Hulit et al. Hulit et al. describes three configurations where a nip is formed between two rolls. In each configuration, an imprinting fabric and a felt are interposed between the rolls. A paper web is carried on the imprinting fabric and imprinted by the imprinting fabric. Hulit then carries the web from this nip on the imprinting fabric. In two embodiments, Hulit then transfers the web from the imprinting fabric to a Yankee drying drum. In the third embodiment, Hulit does not use a Yankee drying drum.

The Hulit arrangement have several disadvantages. First, two sets of nips are required, a first nip to imprint the web and a second nip where the web is transferred to the Yankee drying drum, Hulit recognizes that dryer drums may be utilized instead of, or in addition to, the Yankee drying drum. However, Hulit does not minimize the expense and inconvenience of requiring two separate nips for the configurations relying upon the Yankee drying drum - as most commonly occurs in the art.

Furthermore, by imprinting the paper web in a first operation, and transferring the paper web to the Yankee drying drum in a second operation, Hulit creates caliper in one operation which he destroys in a subsequent operation. Compaction of Hulit's web necessarily occurs between the compression roll and the Yankee dryer. This compaction destroys the caliper that was built in by imprinting the web in the first place.

Another attempt is shown in European Patent 0 526 592 B1 granted April 5, 1995 to Erikson et al. Erikson et al. discloses another two nip configuration. In the first nip, the paper is imprinted between a the press roll and a lower press roll. There, Erikson et

al. dewater the paper by placing the press felt directly against the paper. This allows the press felt to deform into the areas of the imprinting fabric not supported by knuckles, reducing the differential density effects of the compaction caused by the imprinting fabric.

Erikson imprints the paper and transfers it to the Yankee at a lower press roll. The paper is transferred to the Yankee drying drum at this point. However, the second press drum again imprints the paper. The problem presented by the Erikson et al. is that its second nip the imprinting belt is never in registration with the imprinted pattern provided at the first nip. Thus, Erikson unduly compacts the paper and destroys the caliper it creates by imprinting at the first nip.

Furthermore, Erikson et al. like the aforementioned attempts in the art, still requires a complex two nip system. Erikson also requires the press felt loop to be outboard of the imprinting fabric loop. This arrangement creates a very expensive proposition for retrofit to existing machinery, as additional space, drives, etc. are required to add the separate felt loop. The cost of installing such a separate felt loop on an existing papermaking machine is estimated to be in excess of \$10 million.

Commonly assigned U.S. Patent. 5,637,194 issued June 10, 1997 to Ampulski et al., the disclosure of which is incorporated herein by reference, discloses an alternative paper machine embodiment where a felt is positioned adjacent a face of the imprinting member. The imprinting members imprints the molded web and carries it to the Yankee drying drum. Ampulski et al. teaches that the imprinting member is useable for through-air drying and the web is molded into the imprinting member. While Ampulski et al. represents a significant improvement over the prior art, Ampulski et al. still does not provide full contact of the web against the Yankee drying drum.

#### SUMMARY OF THE INVENTION

The invention comprises a papermaking apparatus. The apparatus has first and second rigid surfaces juxtaposed to form a nip therebetween. An imprinting member is interposable in the nip and carries a web. The imprinting member has a sheet side for contacting the web and an opposed backside. The web is in contacting relationship with

the first rigid surface whereby the web can be simultaneously imprinted and transferred to the first rigid surface.

A capillary dewatering member is also interposable in the nip and is contacting relationship with the second rigid surface and with the backside of the imprinting member. A compressive force can be simultaneously applied to the web, the imprinting member and the capillary dewatering member through the nip.

In a preferred embodiment, the nip is formed by two coaxial rolls. One of the rolls may be a Yankee drying drum, the other roll may be a pressure roll and more preferably a vacuum pressure roll.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a vertical side elevational view of a papermaking machine according to the present invention.

Fig. 2 is a fragmentary top plan view of the imprinting member shown in Fig. 1.

Fig. 3 is a vertical sectional view taken along lines 3-3 of Fig. 1.

Fig. 4 is a fragmentary vertical side elevational view of an alternative embodiment of a papermaking machine according to the present invention.

#### DETAILED DESCRIPTION OF THE INVENTION

Referring to Fig. 1, the present invention begins with an aqueous dispersion of fibers deposited from a headbox 10 as is well known in the art. The aqueous dispersion of fibers yields a paper 20 which may be of constant basis weight or may comprise multiple basis weights.

If desired, the paper 20 may have multiple basis weights. Preferably the multiple basis weight paper 20 has two or more distinguishable regions: regions with a relatively high basis weight, and regions with a relatively low basis weight. Preferably the high basis weight regions comprise an essentially continuous network. The low basis weight regions may be discrete. If desired, the paper 20 according to present invention may also comprise intermediate basis weight regions disposed within the low basis weight regions. Such paper 20 may be made according to commonly assigned U.S. patent 5,245,025, issued Sept. 14, 1993 to Trokhan et al., the disclosure of which is incorporated herein by

reference. If the paper 20 has only two different basis weight regions, an essentially continuous high basis weight region, with discrete low basis weight regions disposed throughout the essentially continuous high basis weight region, such paper 20 may be made according to commonly assigned U.S. patents 5,527,428 issued June 18, 1996 to Trokhan et al.; 5,534,326 issued July 9, 1996 to Trokhan et al.; and 5,654,076, issued Aug. 5, 1997 to Trokhan et al., the disclosures of which are incorporated herein by reference.

One may further wish to densify selected regions of the paper 20. Such paper 20 will have both multiple density regions and multiple basis weight regions. Such paper 20 may be made according to commonly assigned U.S. patents 5,277,761, issued Jan. 11, 1994 to Phan et al.; and 5,443,691, issued Aug. 22, 1995 to Phan et al., the disclosures of which are incorporated herein by reference.

The forming wire 15 used to make the aforementioned multibasis weight paper 20 may comprise a plurality of protuberances. The protuberances are upstanding from the plane of the forming wire 15 and are preferably discrete. The protuberances obturate drainage through selected regions of the forming wire 15, producing low and high basis weight regions in the paper 20, respectively. The forming wire 15 for use with the present invention may be made according to commonly assigned U.S. patents 5,503,715, issued Apr. 2, 1996 to Trokhan et al. and 5,614,061, issued March 25, 1997 to Phan et al., the disclosures of which are incorporated herein by reference.

The paper is transferred from the forming wire 15 to an imprinting belt 30. The imprinting belt 30 like the forming wire 15, is macroscopically monoplanar. The plane of the imprinting belt 30 defines its X-Y directions. Perpendicular to the X-Y directions and the plane of the imprinting belt 30 is the Z-direction of the belt 30. Likewise, the paper 20 according to the present invention can be thought of as macroscopically monoplanar and lying in an X-Y plane. Perpendicular to the X-Y directions and the plane of the paper 20 is the Z-direction of the paper 20.

The first surface 31 of the imprinting belt 30 contacts the paper 20 carried thereon. During papermaking, the first surface 31 of the imprinting belt 30 may imprint a pattern onto the paper 20 corresponding to the pattern of a framework 42.

The second surface 32 of the imprinting belt 30 is the machine contacting surface of the belt 10. The second surface 32 may be made with a backside network having passageways therein which are distinct from deflection conduits 46 through the belt 30. The passageways provide irregularities in the texture of the backside of the second surface 32 of the belt 30. The passageways allow for air leakage in the X-Y plane of the belt 30, which leakage does not necessarily flow in the Z-direction through the deflection conduits 46 of the belt 30.

Alternatively, the imprinting belt 30 may have discontinuous knuckles. The discontinuous knuckles made by a particular weave of warp and weft yarns. The paper 20 made on such an imprinting belt will have a like pattern of discrete imprinted areas. Imprinting belts, which are also used for through air drying, and known to be suitable for this purpose are illustrated in commonly assigned U.S. Patents 3,301,746 issued Jan. 31, 1967 to Sanford et al.; 3,905,863 issued Sept. 16, 1975 to Ayers; and 4,239,065 issued Dec. 16, 1982 to Trokhan, the disclosures of which are incorporated herein by reference.

If desired, the imprinting belt 30 used for the present invention may be woven on a Jacquard loom. The Jacquard loom is alleged to have the advantage of providing flexibility in the resulting belt. Examples of belts woven on Jacquard looms are disclosed in U.S. Pat. No. 5,672,248 issued to Farrington.

Preferably, the imprinting belt 30 according to the present invention comprises two primary components, a framework 42 and a reinforcing structure 44. The framework 42 preferably comprises a polymeric resin. The framework 42 and imprinting belt 30 have a first surface 31 which defines the paper contacting side of the belt 30 and an opposed second surface 32 oriented towards the papermaking machine on which the belt 30 is used.

Preferably the framework 42 defines a predetermined pattern, which imprints a like pattern onto the paper 20 of the present invention. A particularly preferred pattern for the framework 12 is an essentially continuous network. If the preferred essentially continuous network pattern is selected for the framework 42, discrete conduits 46 will extend between the first surface 31 and the second surface 32 of the imprinting belt 30. The essentially continuous network surrounds and defines the conduits 46.



The second primary component of the belt 30 according to the present invention is the reinforcing structure 44. The reinforcing structure 44, like the framework 42, has a first or paper facing side and a second or machine facing surface opposite the paper facing surface. The reinforcing structure 44 is primarily disposed between the opposed surfaces of the belt 30 and may have a surface coincident the backside of the belt 30. The reinforcing structure 44 provides support for the framework 42. The reinforcing structure 44 is typically woven, as is well known in the art. The portions of the reinforcing structure 44 registered with the deflection conduits 46 prevent fibers used in papermaking from passing completely through the deflection conduits 46 and thereby reduces the occurrences of pinholes. If one does not wish to use a woven fabric for the reinforcing structure 44, a nonwoven element, screen, net, or a plate having a plurality of holes therethrough may provide adequate strength and support for the framework 42 of the present invention.

The imprinting belt 30 according to the present invention may be made according to any of commonly assigned U.S. Patents: 4,514,345, issued April 30, 1985 to Johnson et al.; 4,528,239, issued July 9, 1985 to Trokhan; 5,098,522, issued March 24, 1992; 5,260,171, issued Nov. 9, 1993 to Smurkoski et al.; 5,275,700, issued Jan. 4, 1994 to Trokhan; 5,328,565, issued July 12, 1994 to Rasch et al.; 5,334,289, issued Aug. 2, 1994 to Trokhan et al.; 5,431,786, issued July 11, 1995 to Rasch et al.; 5,496,624, issued March 5, 1996 to Stelljes, Jr. et al.; 5,500,277, issued March 19, 1996 to Trokhan et al.; 5,514,523, issued May 7, 1996 to Trokhan et al.; 5,554,467, issued Sept. 10, 1996, to Trokhan et al.; 5,566,724, issued Oct. 22, 1996 to Trokhan et al.; 5,624,790, issued April 29, 1997 to Trokhan et al.; and 5,628,876, issued May 13, 1997 to Ayers et al., the disclosures of which are incorporated herein by reference.

Preferably, the framework 42 extends outwardly from the reinforcing structure 44 a distance of less than about 0.15 millimeters, more preferably less than about 0.10 millimeters and still more preferably less than about 0.05 millimeters. Still more preferably the patterned framework 42 is approximately coincident the elevation of the reinforcing structure 44. By having the patterned framework 42 extending outwardly such a small distance from the reinforcing structure 44. By having the patterned framework 42 extending outwardly such a small distance from the reinforcing structure 44, a softer

product may be produced. Specifically, this provides for the absence of deflection or molding of the paper 20 into the imprinting belt 30 as occurs in the prior art. Thus, the resulting paper 20 will have a smoother surface and less tactile roughness.

Furthermore, by having the framework 42 extend outwardly from the reinforcing structure 44 such a short distance, the reinforcing structure 44 will contact the paper at top surface knuckles disposed within the deflection conduits 46. This arrangement further compacts the paper 20 at the points coincident the knuckles against the Yankee drying drum 70, decreasing the XY spacing between compacted regions.

Thus, greater contact between the paper 20 and the Yankee 70 occurs. As noted above, one of the benefits of the present invention is that the imprinting of the paper 20 and transfer to the Yankee 70 occur simultaneously, eliminating the multioperational steps of the prior art. By transferring substantially full contact of the paper 20 to the Yankee 70 - rather than just compacted knuckles as occurs in the prior art - full contact drying can be obtained. Furthermore, by simultaneously imprinting the paper 20 and transferring it to the Yankee 70 caliper is maintained.

The prior art attempts imprinted in one operation and transferred to the Yankee 70 in a second operation. The second operation, with its own separation nip, compacts the paper 20 - destroying the caliper imparted to the paper 20 at the first nip. The present operation simultaneously imprints and transfers thus obviating this problem.

The paper 20 may also be foreshortened, as is known in the art. Foreshortening can be accomplished by creping the paper 20 from a rigid surface, and preferably from a cylinder. A Yankee drying drum 70 is commonly used for this purpose. Creping is accomplished with a doctor blade as is well known in the art. Creping may be accomplished according to commonly assigned U.S. Patent 4,919,756, issued April 24, 1992 to Sawdai, the disclosure of which is incorporated herein by reference. Alternatively or additionally, foreshortening may be accomplished via wet microcontraction as taught in commonly assigned U.S. Patent 4,440,597, issued April 3, 1984 to Wells et al., the disclosure of which is incorporated herein by reference. The creping blade will selectively and differentially crepe the compacted and relatively noncompacted areas of the paper 20.

In the present invention, a conventional felt 60 is juxtaposed with the backside of the imprinting belt 30. The conventional felt 60 has a surface batting with a denier of less than 5, and preferably less than 3. This surface batting contacts the imprinting belt 30 during papermaking. The felt 60 may have a basis weight of 200 to 1400 grams per square meter. Preferably, the felt 60 does not have a separate pattern thereon, so that the first surface 31 of the felt 70 directly and completely contacts the backside of the imprinting belt 30. This contact assists in water removal from the imprinting belt 30 and hence from the paper 20. However, if desired, the felt 60 may be provided with a patterned framework thereon, as disclosed in the aforementioned patents incorporated herein by reference.

It is important that a hydraulic connection be made, in turn, between the paper 20, the imprinting belt 30, and the felt 60. The hydraulic connection can be improved in several ways. First, the felt 60 can be compacted. Compacting the felt 60 decreases the average volume of the pores of the felt 60. Preferably, the felt 60 will have an average pore volume distribution of less than 50 microns.

A suitable press felt 60 is an Ampfex 2 manufactured by the Appleton Mills Company of Appleton, Wisconsin. Such a felt 60 has a thickness of about 2-5 millimeters, and a basis weight of 800 to 2000 grams per square meter, and an average density of 0.16 to 1.0 grams per cubic centimeter. The felt 60 may have an air permeability between about 5 and about 300 SCFM per square foot, with an air impermeability of less than 50 SCFM per square foot being preferred for use with the present invention.

Additionally to improve the hydraulic connection, the imprinting belt 30 may have a batting needled therethrough. The batting may extend outwardly from both the machine facing surface 32 and the sheet facing surface 31 of the imprinting belt 30. More preferably the batting extends outwardly from the backside of the belt 30 so that intimate contact with the felt 60 is provided. If desired, the imprinting member 30 having the batting thereon may be compacted to decrease its average pore volume distribution.

Compaction to decrease pore volume distribution of either a batted imprinting member 30 or the felt 60 can be accomplished by a calendar nip, as is known in the art. Preferably, the average pore volume distribution monotonically decreases from the paper 20 to the added imprinting member 30 to the capillary felt 60. Such a monotonic decrease

provides a thermodynamic attraction which assists in removing water from the paper 20 to be dried.

If desired, other capillary dewatering members may be used in place of the felt 60 described above. For example, a foam capillary dewatering member may be selected. Preferably such a foam has an average pore size of less than 50 microns. Suitable foams may be made in accordance with commonly assigned U.S. Patent No. 5,260,345 issued Nov. 9, 1993 to DesMarais et al. and 5,625,222 issued July 22, 1997 to DesMarais et al., the disclosures of which are incorporated herein by reference.

Alternatively, a limiting orifice drying medium may be used as capillary dewatering member. Such a medium may be made of various laminae, superimposed in face to face relationship. The laminae have an interstitial flow area smaller than that of the interstitial areas between fibers in the paper. A suitable limiting orifice drying member may be made in accordance with commonly assigned U.S. Patents 5,625,961 issued May 6, 1997 to Ensign et al. and 5,274,930 issued Jan. 4, 1994 to Ensign et al., the disclosures of which are incorporated herein by reference.

The felt 60, imprinting member 30, and paper 20 are interposed in a nip. Preferably, the nip is formed between two coaxial rolls. More preferably, one of the rolls is heated, and still more preferably comprises a heated Yankee drying drum 70. The other of the rolls 35 may be a vacuum pressure roll.

The felt 60, imprinting belt 30 and paper 20 are interposed in the nip such that the paper 20 is adjacent the heated roll, preferably the heated drying drum and more preferably a Yankee drying drum 70. The imprinting belt 30 is juxtaposed with and in contacting relationship with the paper 20. The felt 60 is juxtaposed and in contacting relationship with the backside of the imprinting belt 30 and the periphery of the other, or second, roll 35.

If desired, a vacuum may be applied through the second roll 35 to the felt. This vacuum assists in water removal from the felt 60, and hence from the paper 20. The second roll 35 may be a vacuum pressure roll. Preferably, a steam box is disposed opposite the vacuum pressure roll 35. A steam box ejects steam through the paper 20. As the steam

passes through the paper 20, it reduces the viscosity of water contained therein, promoting better drying. The steam is collected by the vacuum pressure roll 35.

If further desired, a vacuum box may be substituted for the vacuum pressure roll 35. The vacuum box will allow for a positive draw of air, and hence water, through the paper 20 at the position where the paper 20 is transferred to the Yankee drying drum 70.

Of course, one of ordinary skill will recognize that the simultaneous imprinting, dewatering and transfer operations may occur in embodiments other than these requiring a Yankee drying drum. For example, two flat surfaces may be juxtaposed together to form an elongate nip therebetween. Alternatively, two rolls may be utilized, neither of which roll is heated. The rolls may be, for example, part of a calendar stack, or an operation which prints a functional additive onto the surface of the web. Functional additives include: lotions emollients, dimethicones, softeners, perfumes, menthols, etc. which are well known in the art.

Referring to Fig. 4, if desired, the capillary dewatering member 60 may comprise an extended loop. The extended loop is nested with the imprinting member 30 as illustrated in Fig. 1. However, the extended nested loop of Fig. 4 provides the advantage that dewatering can occur at a first nip, with subsequent dewatering and transfer occurring at a second nip. However, the total number of clothings required for the embodiment of Fig. 4 does not increase over that shown in Fig. 1.

One of ordinary skill will recognize that many other variations and permutations are feasible. For example, a single roll and an elongate flat surface may be combined to form a nip therebetween. However, it is only with the present invention that the simultaneous three functions of dewatering the web and/or the capillary dewatering member by compression, imprinting the web, and transferring the web from the imprinting member can simultaneously occur. All such apparatuses and processes are within the scope of the appended claims.

What is claimed is:

1. A papermaking apparatus comprising:

First and second rigid surfaces juxtaposed to form a nip therebetween;

an imprinting member interposable in said nip and carrying a web thereon, said imprinting member having a sheet side for contacting a web during papermaking and a back side opposed thereto;

said web being in contacting relationship with said first rigid surface, whereby said web can be simultaneously imprinted and transferred to said first rigid surface; and

a capillary dewatering member interposable in said nip in contacting relationship with said second rigid surface, said capillary dewatering member being disposed in contacting relationship with said backside of said imprinting member, whereby a compressive force can be applied to said web, said imprinting member, and said capillary dewatering member in said nip.

2. An apparatus according to claim 1, wherein said nip is formed by two coaxial rolls juxtaposed to form a nip therebetween, and preferably wherein one of said rolls is a Yankee drum.

3. An apparatus according to claim 2, wherein one of said rolls applies a vacuum to said capillary dewatering member.

4. An apparatus according to claim 1, 2 and 3, wherein said capillary dewatering member comprises a woven felt and preferably said capillary dewatering felt has a denier of less than about 5.

5. An apparatus according to claims 1, 2, 3 and 4, wherein said imprinting member comprises a woven belt having a Jacquard weave.
6. An apparatus according to claim 5, wherein said imprinting member comprises a reinforcing structure and a patterned framework disposed thereon, said patterned framework being oriented towards said web while said web and said imprinting member are in said nip.
7. An apparatus according to claim \_\_\_, wherein said patterned framework extends outwardly from said foraminous belt, a distance less than 0.15 millimeters and preferably a distance less than 0.05 millimeters.
8. A papermaking apparatus comprising:
  - a Yankee drying drum and a pressure roll juxtaposed to form a nip therebetween, an imprinting member interposable in said nip, said imprinting member comprising a reinforcing element having a patterned framework extending outwardly therefrom, said patterned framework contacting and imprinting said web in said nip, said web simultaneously contacting and being transferred to said Yankee drying drum in said nip; and
  - a felt, said felt being juxtaposed with said pressure roll in said nip, whereby said felt can dewater said imprinting belt in said nip.
9. A process of removing water from a web, said process comprising the steps of
  - providing a first roll and a second roll juxtaposed together to form a nip therebetween;
  - providing a cellulosic web to be dried;

providing an imprinting member having a sheet side for imprinting said web and a backside opposed thereto;  
placing said cellulosic web on said imprinting member;  
providing a capillary dewatering member;  
juxtaposing said capillary dewatering member with said backside of said imprinting member;  
interposing said web, said capillary dewatering member and said imprinting member in said nip, whereby a first said roll is interposing said web, said capillary dewatering member and said imprinting member in said nip with said web in contacting relationship with said first roll and said capillary dewatering member in contacting relationship with second roll; whereby water may be removed from said imprinting member by capillary action;  
imprinting said web with said imprinting member; and simultaneously transferring said web to said first roll.

- 10.A process according to claim 9, wherein said paper is imprinted by a patterned framework with a high density pattern corresponding to said framework, said patterned framework being associated with said imprinting member, preferably comprising an essentially continuous network.



1/2




Fig. 1




Fig. 2




Fig. 3

2/2




Fig. 4

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/IB 99/00418

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 6 021F11/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 6 021F		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 637 194 A (AMPULSKI ET AL) 10 June 1997 see the whole document ---	1-4, 6, 8-10
X	US 3 537 954 A (JUSTUS) 3 November 1970 see the whole document ---	1-4, 9
X	FR 2 388 076 A (EBELING ET TURUNEN) 17 November 1978 see the whole document -----	1-4, 9
<input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search  25 June 1999		Date of mailing of the international search report  02/07/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  De Rijck, F

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 99/00418

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5637194 A	10-06-1997	US 5580423 A	03-12-1996
		US 5846379 A	08-12-1998
		US 5861082 A	19-01-1999
		US 5795440 A	18-08-1998
		US 5776307 A	07-07-1998
		US 5855739 A	05-01-1999
		US 5904811 A	18-05-1999
		AT 177490 T	15-03-1999
		AU 1005099 A	25-02-1999
		AU 701610 B	04-02-1999
		AU 1374595 A	10-07-1995
		BR 9408381 A	26-08-1997
		CA 2178586 A	29-06-1995
		CN 1141658 A	29-01-1997
		CZ 9601835 A	13-11-1996
		DE 69417068 D	15-04-1999
		EP 0741820 A	13-11-1996
		ES 2128705 T	16-05-1999
		FI 962597 A	26-07-1996
		JP 9506937 T	08-07-1997
		NO 962572 A	19-08-1996
		WO 9517548 A	29-06-1995
US 3537954 A	03-11-1970	NONE	
FR 2388076 A	17-11-1978	FI 771295 A	23-10-1978
		BE 866262 A	14-08-1978
		BR 7802481 A	05-12-1978
		CA 1116452 A	19-01-1982
		CH 627805 A	29-01-1982
		DE 2816581 A	02-11-1978
		GB 1589800 A	20-05-1981
		JP 53134907 A	25-11-1978
		SE 7804589 A	23-10-1978